



pindo deli 
paper products

FO/0/01/1
Rev : 1

UNCONTROLLED COPY

SPECIFICATION	DOC. NO.	SP/6/204/1046
	REVISION	1
	DATE OF ISSUE	22/04/2009
	PAGE	1 OF 1
	TITLE : CARBONLESS PAPER CFB 50, 53, 60 & 75 GSM (R) IMPRESSION 2000	

NO	PARAMETER	UNIT	CFB 50	CFB 53	CFB 60	CFB 75	TEST METHOD
1	Basis Weight	g/m ²	47 - 51	53 ± 2	60 ± 2	72 - 76	ISO 536: 1995
2	Thickness	micron	68 ± 3	73 ± 3	82 ± 3	100 ± 3	ISO 534: 2005
3	Bendtsen Roughness	ml/min	Max. 150	Max. 150	Max. 190	Max. 200	ISO 8791-2: 1990
4	Frictional Smudge	%	Max. 500	Max. 500	Max. 500	Max. 500	
5	Copy Intensity	%	Max. 7	Max. 7	Max. 7	Max. 7	
		2 nd 3 rd 4 th 5 th 6 th	Min. 29 - - Min. 27 Min. 26	Min. 29 - - Min. 27 Min. 26	Min. 29 - - Min. 27 Min. 26	Min. 29 Min. 27 Min. 26 -	- -


Note: TS = Top Side BS = Bottom Side Printer Type for Intensity : EPSON LQ - 2180 Standard Resolution 180 x 180 dpi

Prepared By:



Sec. Head of QC
Date: 21/4/2009

Approved By:



Production Manager
Date: 22/4/2009



Head of Tech. Division
Date: 22/4/2009